

MILLSTOCK STAINLESS LIMITED
 FUSION HOUSE
 THE CRESCENT
 WILLENHALL
 WEST MIDLANDS WV13 2QR
 Tel: +44 (0) 1902 409 409
 Fax: +44 (0) 1902 409 411
 Email: sales@millstockstainless.com

nauticalALLOY 22HS

Chemical Composition	C	Si	Mn	P	S	Cr	Ni	Mo	N
% values (Min)	≤	≤	4.00	≤	≤	20.50	11.50	1.50	0.20
% values (Max)	0.060	1.0	6.00	0.04	0.030	23.50	13.50	3.00	0.40
Mechanical Properties	Proof Strength Rp0.2		Tensile Strength		Elong.		Red of Area %	Hardness BHN (Min)	
Metric units (Mpa-N/mm2)	>725		825 - 1150		15		45	<340	
Imperial units (mpa)	>105		120 - 165		15		45	<340	
Related Specifications	UNS S20910		XM-19HS		Nitronic 50 [®]		1.3964		

- Nauticalloy 22HS combines high strength with the best corrosion resistance to offer the ultimate Marine Shaft material, Nauticalloy 22HS is a Non Magnetic Alloy Steel

- Telephone: +44 (0) 1902 409 409
- Fax: +44 (0) 1902 409 411
- Email: sales@millstockstainless.com
- Web: www.millstockstainless.com
www.nauticalloy.com